



Forton VF-774

Technical Data

May 8, 2007

Description

- Water based, all acrylic co-polymer emulsion formulated to comply with PCI MNL 130, Quality Control Manual, Appendix L for curing admixtures used in GFRC.
- VF-774 also has long term natural ageing data to verify that its use in GFRC composites improves aged flexural properties.
- VF-774 can be used in precast concrete to reduce absorption, maintain color uniformity, and reduce or eliminate crazing and efflorescence.
- It is also used in concrete repair products and bonding agents due to its superior adhesive properties.

Physical Data (also MNL 130 specification)

- | | |
|---|------------------------|
| ○ Solids by weight | 51% ($\pm 1\%$) |
| ○ Viscosity 23°C (Brookfield, Spindle 2/50 rpm) | 100 – 300 cps |
| ○ pH | 8 – 10 |
| ○ Density at 20°C | 1055 kg/m ³ |
| ○ Tg | 11°C |
| ○ Particle Size | .1300 - .2500 |
| ○ Grit | 0 – 50 ppm |

Storage

- Forton VF-774 should be stored in a closed container, in a dry environment at storage temperatures between 5°C and 30°C.
- Storage should be enclosed, out of direct sun light and away from direct sources of heat.

Shelf Life

- With proper storage conditions the normal shelf life will typically be 9 months.

www.Ball-Consulting-Ltd.com

2301 Duss Avenue, Ambridge, PA 15003, Phone: 800-225-2673, Fax 724-266-1504, email: ball@ball-consulting-ltd.com
4665 South Ash, Suite G15, Tempe, AZ 85282, Phone: 888-967-7727, Fax: 480-967-8113, email: sshafer@ball-consulting-ltd.com