



# Fast Stone LT<sup>®</sup>

## Suggested Mix Calculations

### Fast Stone LT<sup>®</sup> 20W <sup>(1)</sup>

	<u>5 gal pail</u>	<u>40 lb. bag</u>
Fast Stone LT <sup>®</sup> 20W	20	40
VF-774	1.5	3
Water	4	8
	<hr/>	<hr/>
	25.5	51
Plasticizer (fluid oz)	1.5	3
ADVA <sup>®</sup> Cast 555		
AR Fiber (1.5%)	0.4	0.8
	<hr/>	<hr/>
	25.9	51.8

(1) The basic mix design for all Fast Stone<sup>®</sup> LT products is the same. Fast Stone<sup>®</sup> LT 20W is used as an example only.

[www.Ball-Consulting-Ltd.com](http://www.Ball-Consulting-Ltd.com)

338 Fourteenth Street, Ambridge, PA 15003, Phone: 800-225-2673, Fax 724-266-1504, email: ball@ball-consulting-ltd.com  
4665 South Ash, Suite G15, Tempe, AZ 85282, Phone: 888-967-7727, Fax: 480-967-8113, email: sshafer@ball-consulting-ltd.com