



Fast Stone[®]

Suggested Mix Calculations

Fast Stone[®] 30W ⁽¹⁾

	<u>5 gal Pail</u>	<u>50 lb. Bag</u>
Fast Stone [®]	12.50	50
Sand	11.25	45
VF-774	1.38	5.5
Water	<u>3.5</u>	<u>14</u>
	28.63	114.5
Plasticizer (fluid oz) ADVA [®] 140	0.5	2
AR Fiber (1.5%)	<u>0.42</u>	<u>1.69</u>
	29.55	116.19

(1) The basic mix design for all Fast Stone[®] products is the same. Fast Stone[®] 30W is used as an example only.

www.Ball-Consulting-Ltd.com

338 Fourteenth Street, Ambridge, PA 15003, Phone: 800-225-2673, Fax 724-266-1504, email: ball@ball-consulting-ltd.com
4665 South Ash, Suite G15, Tempe, AZ 85282, Phone: 888-967-7727, Fax: 480-967-8113, email: sshafer@ball-consulting-ltd.com